

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
15 September 2005 (15.09.2005)

PCT

(10) International Publication Number
WO 2005/085347 A1

(51) International Patent Classification⁷: **C08L 67/00**,
23/00, 23/08, 67/02, 67/03, 67/04

(74) Agents: **NISHIKAWA, Yoshikiyo** et al.; Hokuto Patent
Attorneys Office Umeda-Daichiseimei Bldg. 5th Floor,
12-17, Umeda 1-chome, Kita-ku, Osaka-shi, Osaka
5300001 (JP).

(21) International Application Number:
PCT/JP2005/004168

(22) International Filing Date: 3 March 2005 (03.03.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2004-068009 10 March 2004 (10.03.2004) JP

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG,
KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG,
MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH,
PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(71) Applicants (*for all designated States except US*): **MAT-
SUSHITA ELECTRIC WORKS, LTD.** [JP/JP]; 1048,
Oaza-Kadoma, Kadoma-shi, Osaka, 5718686 (JP). **SUM-
ITOMO CHEMICAL COMPANY, LIMITED** [JP/JP];
27-1, Shinkawa 2-chome, Chuo-ku, Tokyo, 1048260 (JP).

(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **IKEGAWA,**
Naoto [JP/JP]; c/o Matsushita Electric Works, Ltd.,
1048, Oaza-Kadoma, Kadoma-shi, Osaka 5718686 (JP).
OKAMOTO, Satoshi [JP/JP]; c/o Sumitomo Chemical
Company, Limited, 6, Kitahara, Tsukuba-shi, Ibaraki
3003294 (JP). **KATAGIRI, Shiro** [JP/JP]; c/o Sumitomo
Chemical Company, Limited, 6, Kitahara, Tsukuba-shi,
Ibaraki 3003294 (JP).

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: RESIN MOLDED ARTICLE WITH REDUCED DIELECTRIC LOSS TANGENT AND PRODUCTION METHOD THEREFOR

(57) Abstract: A resin molded article having a reduced dielectric loss tangent is provided. This resin molded article is obtained by performing a heat treatment to a resin composition comprising a liquid-crystalline polyester and an epoxy-group containing ethylene copolymer at a temperature lower than a flow-beginning temperature of the liquid-crystalline polyester, preferably at a temperature between a lower limit temperature calculated by subtracting 120°C from the flow-beginning temperature and an upper limit temperature calculated by subtracting 20°C from the flow-beginning temperature. This resin molded article has a smaller dielectric loss tan



WO 2005/085347 A1